



Technical Data Sheet

OrangeDECO HoloMe Gold

Product Description

Go for gold! This hologram foil impresses with its clear gold tone, but still shines in all the colors of the rainbow. With our orangeJet HoloMe Gold, your campaign or lettering will be an absolute eye-catcher and therefore also a sales promoter.

Application

An outstanding hologram effect in a clear, elegant gold tone enlivens any decoration on walls and glass.

Material

PVC calendered, hologram effect

Colour / Finish

gold / glossy

Thickness (without liner and adhesive, ISO 4593)

100 µm

Adhesive

solvent polyacrylate, clear, permanent

Adhesive Power (FINAT TM 1)

8 N/25 mm

Release Paper

single PE, 120g

Weight

280 g/m²

Printability

solvent, eco-solvent, latex, UV-gel, UV-cured

Application Temperature

>10°C / >50°F

Temperature Resistance

-30°C - +60°C / -22°F - +140°F

Dimensional Stability (FINAT TM 14)

Shrinkage ≤ 1,5 mm

Tensile Strength (DIN EN ISO 527)

along: 30,78 Mpa / across: 20,76 Mpa

Elongation at Break (DIN EN ISO 527)

along: 301,86% / across: 212,24%

Indoor Durability

18 months

Shelf Life / Storage Conditions

18 months in original packaging

18°C - 25°C / 64°F - 77°F, 40 - 60 % relative humidity

Technisches Datenblatt

OrangeDECO HoloMe Gold

Produktbeschreibung

Go for Gold! Diese Hologramm-Folie besticht durch ihren klaren Goldton, strahlt aber dennoch in allen Regenbogenfarben. Ihre Kampagne oder Beschriftung wird mit unserem orangeJet HoloMe Gold zu einem absoluten Hingucker und damit auch Verkaufsförderer.

Anwendung

Ein herausragender Hologramm-Effekt in einem klaren edlen Goldton belebt jede Dekoration an der Wand und auf Glas.

Material

PVC kalandriert, Hologrammeffekt

Farbe / Oberfläche

gold / glänzend

Dicke (ohne Liner und Klebstoff, ISO 4593)

100 µm

Haftklebstoff

Solvent Polyacrylat, transparent, permanent

Klebkraft (FINAT TM 1)

8 N/25 mm

Abdeckung/Liner

single PE, 120g

Gewicht

280 g/m²

Bedruckbarkeit

solvent, eco-solvent, Latex, UV-Gel, UV-härtend

Verarbeitungstemperatur

>10°C / >50°F

Temperaturbeständigkeit

-30°C - +60°C / -22°F - +140°F

Formbeständigkeit (FINAT TM 14)

Schrumpf ≤ 1,5 mm

Reißfestigkeit (DIN EN ISO 527)

längs: 30,78 Mpa / quer: 20,76 Mpa

Reißdehnung (DIN EN ISO 527)

längs: 301,86% / quer: 212,24%

Haltbarkeit im Innenbereich

18 Monate

Lagerzeit / Lagerbedingungen

18 Monate in Originalverpackung

18°C - 25°C / 64°F - 77°F, 40 - 60 % relative Luftfeuchtigkeit