

Technical Data Sheet

OrangeDECO HoloMe Satin

Product Description

Everyone knows hologram foils. The unique shimmer in all the colors of the rainbow is popular everywhere. Now, with the orangeJet HoloMe Satin, the silver effect is available in a very elegant satin - an upgrade on the upgrade, so to speak.

Application

A silver hologram effect with a sophisticated satin finish enlivens any wall or glass decoration.

Material

PVC calendered, hologram effect

Colour / Finish

silver / semi-matt

Thickness (without liner and adhesive, ISO 4593)

100 µm

Adhesive

solvent polyacrylate, clear, permanent

Adhesive Power (FINAT TM 1)

8 N/25 mm

Release Paper

single PE, 120g

Weight

280 g/m²

Printability

solvent, eco-solvent, latex, UV-gel, UV-cured

Application Temperature

>10°C / >50°F

Temperature Resistance

-30°C - +60°C / -22°F - +140°F

Dimensional Stability (FINAT TM 14)

Shrinkage ≤ 1,5 mm

Tensile Strength (DIN EN ISO 527)

along: 30,78 Mpa / across: 20,76 Mpa

Elongation at Break (DIN EN ISO 527)

along: 301,86% / across: 212,24%

Indoor Durability

18 months

Shelf Life / Storage Conditions

18 months in original packaging

18°C - 25°C / 64°F - 77°F, 40 - 60 % relative humidity

Technisches Datenblatt

OrangeDECO HoloMe Satin

Produktbeschreibung

Hologrammfolien kennt jeder. Der einzigartige Schimmer in allen Regenbogenfarben ist überall beliebt. Jetzt gibt es mit dem orangeJet HoloMe Satin den silbernen Effekt in einem ganz edlen Satin - quasi ein Upgrade auf das Upgrade.

Anwendung

Ein silberner Hologramm-Effekt mit einem edlen Satin-Finish belebt jede Dekoration an Wand und auf Glas.

Material

PVC kalandriert, Hologrammeffekt

Farbe / Oberfläche

silber / seidenmatt

Dicke (ohne Liner und Klebstoff, ISO 4593)

100 µm

Haftklebstoff

Solvent Polyacrylat, transparent, permanent

Klebkraft (FINAT TM 1)

8 N/25 mm

Abdeckung/Liner

single PE, 120g

Gewicht

280 g/m²

Bedruckbarkeit

solvent, eco-solvent, Latex, UV-Gel, UV-härtend

Verarbeitungstemperatur

>10°C / >50°F

Temperaturbeständigkeit

-30°C - +60°C / -22°F - +140°F

Formbeständigkeit (FINAT TM 14)

Schrumpf ≤ 1,5 mm

Reißfestigkeit (DIN EN ISO 527)

längs: 30,78 Mpa / quer: 20,76 Mpa

Reißdehnung (DIN EN ISO 527)

längs: 301,86% / quer: 212,24%

Haltbarkeit im Innenbereich

18 Monate

Lagerzeit / Lagerbedingungen

18 Monate in Originalverpackung

18°C - 25°C / 64°F - 77°F, 40 - 60 % relative Luftfeuchtigkeit