



Technical Data Sheet

OrangeFLOOR Quick&Safe White

Product Description

A directly printable floor film for short-term use that won't break the budget. With orangeFloor Quick & Safe, you can make your campaign exactly as the name suggests: Quick to implement and safe!

Application

Direct printable floorgraphic material for short-term campaigns

Material

PVC calendered, rough

Colour / Finish

white / semi-matt

Thickness (without liner and adhesive, ISO 4593)

180 ± 10 µm

Adhesive

solvent polyacrylate, clear, permanent

Adhesive Power (FINAT TM 1)

16 N/25 mm

Release Paper

single PE, 140g

Weight

380 g/m²

Printability

solvent, eco-solvent, latex, UV-gel, UV-cured, SilkScreen

Certificates

R10, EN13501 flame-retardant

Application Temperature

>10°C / >50°F

Temperature Resistance

-30°C - +60°C / -22°F - +140°F

Dimensional Stability (FINAT TM 14)

Shrinkage ≤ 1,5 mm

Tensile Strength (DIN EN ISO 527)

along: 21.2 Mpa / across: 20.1 Mpa

Elongation at Break (DIN EN ISO 527)

along: 275% / across: 292%

Indoor Durability

3 months

Shelf Life / Storage Conditions

18 months in original packaging

18°C - 25°C / 64°F - 77°F, 40 - 60 % relative humidity

Technisches Datenblatt

OrangeFLOOR Quick&Safe White

Produktbeschreibung

Eine direkt bedruckbare Fußbodenfolie für den kurzfristigen Einsatz, die nicht jedes Budget sprengt. Mit dem orangeFloor Quick & Safe machen Sie Ihre Kampagne genau so, wie es der Name vorgibt: Schnell umsetzbar und sicher!

Anwendung

Direkt bedruckbare Fußbodenfolie für den kurzfristigen Einsatz

Material

PVC kalandriert, rau

Farbe / Oberfläche

weiß / seidenmatt

Dicke (ohne Liner und Klebstoff, ISO 4593)

180 ± 10 µm

Haftklebstoff

Solvent Polyacrylat, transparent, permanent

Klebkraft (FINAT TM 1)

16 N/25 mm

Abdeckung/Liner

single PE, 140g

Gewicht

380 g/m²

Bedruckbarkeit

solvent, eco-solvent, Latex, UV-Gel, UV-härtend, SilkScreen

Zertifikate

R10, EN13501 flame-retardant

Verarbeitungstemperatur

>10°C / >50°F

Temperaturbeständigkeit

-30°C - +60°C / -22°F - +140°F

Formbeständigkeit (FINAT TM 14)

Schrumpf ≤ 1,5 mm

Reißfestigkeit (DIN EN ISO 527)

längs: 21.2 Mpa / quer: 20.1 Mpa

Reißdehnung (DIN EN ISO 527)

längs: 275% / quer: 292%

Haltbarkeit im Innenbereich

3 Monate

Lagerzeit / Lagerbedingungen

18 Monate in Originalverpackung

18°C - 25°C / 64°F - 77°F, 40 - 60 % relative Luftfeuchtigkeit